

Ammonium Polyvanadate APV

Properties

Orange powder

Application

- Additives for ceramic pigments
- Catalysts



Chemical analysis

	Standard	Technical
V ₂ O ₅	min. 89,0 %	min. 89,6 %
V	min. 49,9 %	min. 50,2 %
H ₂ O	< 1,0 %	< 1,0 %
Fe	< 0,1 %	< 0,05 %
K	< 0,4 %	< 0,3 %
P	< 0,03 %	< 0,01 %
Si	< 0,1 %	< 0,05 %

Physical parameter

Particle size	max. 1,2 mm
Bulk density	650 ± 100 kg/m ³
Material density	3360 kg/m ³

Packing:

- Steeldrums with 120 kgs resp. 50 kgs net
- Other packing on request