

# CERIUM-(III)-FLUORIDE $CeF_3$

## Properties

White powder

## Application

- Dopants for carbon electrodes
- Refractory ceramics



## Chemical analysis

		<b>99,9 %</b>
<b><u>Material base</u></b>		
TREO*		typ. 85,0%
F		typ. 23,0 %
Fe <sub>2</sub> O <sub>3</sub>		< 200 ppm
<b><u>TREO base</u></b>		
CeO <sub>2</sub>		min. 99,9 %
Total remaining RE-Oxides		max. 0,1 %

\*TREO = Total Rare Earth Oxide

## Packing

- Plastic boxes with 1, 5 or 10 kgs net
- Plastic or steeldrums with 25 kgs resp. 50 kgs net
- Other packing on request