

Cobalt Aluminate Pigment $CoAl_2O_4$

Properties

- Blue powder

Anwendung

- Pigment for colouring crystal glass

Chemical Analysis

Co	29,7 – 32,3 %
Al	balance
Fe	< 200 ppm
Ca	< 250 ppm
Mg	< 100 ppm
Si	< 500 ppm
Ti	< 50 ppm
Pb	< 10 ppm
Bi	< 50 ppm
Sb	< 50 ppm
Na	< 200 ppm
K	< 100 ppm
Zn	< 10 ppm
Zr	< 50 ppm

Physical parameters

Surface Area (BET)	1 - 4 m ² /g
PSD (Microtrac)	
D10	0,2 - 0,7 µm
D50	1,0 - 3,0 µm
D90	3,0 - 7,0 µm



Packaging

- 25 or 50 kg steeldrums