

FERRO MOLYBDENUM 70 (FeMo 70)

Properties

- Density: approx. 8,8 g/cm³.
- Bulk density: approx. 4,0 g/cm³.
- Melting range: 1850 – 1950 °C.
- Particle sizes: 5-50 mm, 1-5 mm, 0-1 mm.
- Powder: grain size distribution on request.

Application

- HSLA steels
- Structural steels
- High speed/tool steels
- Acid resistant steels
- Steel casting
- Welding electrodes
- Super alloys

Chemical Analysis

Mo	65 – 74 %
C	max. 0,10 %
Si	max. 2,00 %
P	max. 0,05 %
S	max. 0,15 %
Cu	max. 0,50 %



Packing

- Big bags – net weight 1.000 kg
- Steel drums – net weight 50 - 500 kg
identification colour: black

General Remarks

- Other specifications,
sizes or packaging types on request