

LANTHANUM FLUORIDE *LaF3*

Properties

White powder

Application

- Manufacture of optical glass



Chemical analysis

		99,99 %
<u>Material base</u>		
TREO*		typ. 82,0 %
F		typ. 22,0 %
Fe ₂ O ₃		< 200 ppm
<u>TREO base</u>		
La ₂ O ₃		min. 99,99 %
Total remaining RE-Oxides		max. 100 ppm

*TREO = Total Rare Earth Oxide

Packing

- Plastic boxes with 1, 5 or 10 kgs net
- Plastic or steeldrums with 25 kgs resp. 50 kgs net
- Other packing on request